

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 10/00, 4/64, C07F 17/00		A1	(11) International Publication Number: WO 96/00244
			(43) International Publication Date: 4 January 1996 (04.01.96)
(21) International Application Number: PCT/US95/07715		(81) Designated States: AU, CA, FI, JP, KR, MX, NO, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 26 June 1995 (26.06.95)			
(30) Priority Data: 08/265,533 24 June 1994 (24.06.94) US 08/412,810 29 March 1995 (29.03.95) US 08/487,255 7 June 1995 (07.06.95) US		Published With international search report.	
(71) Applicant: EXXON CHEMICAL PATENTS INC. [US/US]; 5200 Bayway Drive, Baytown, TX 77520 (US).			
(72) Inventor: CANICH, Jo, Ann, Marie; Apartment 808, 900 Henderson Avenue, Houston, TX 77058 (US).			
(74) Agents: SMITH, Charles, E. et al.; Exxon Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US).			
(54) Title: MONOCYCLOPENTADIENYL METAL COMPOUNDS FOR ETHYLENE- α -OLEFIN COPOLYMER PRODUCTION CATALYSTS			
(57) Abstract Described are certain monocyclopentadienyl Group IV B metal compounds, catalyst systems comprising such monocyclopentadienyl metal compounds and an activator, and a process using such catalyst systems for the production of polyolefins, particularly high molecular weight ethylene- α -olefin copolymers having a high level of α -olefin incorporation.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

MONOCYCLOPENTADIENYL METAL COMPOUNDS
FOR ETHYLENE- α -OLEFIN-COPOLYMER
PRODUCTION CATALYSTS

5 This is a continuation-in-part of US Serial No. (not yet assigned),
filed June 6, 1995 (Atty Docket No. 94B032A/2); which is a continuation
10 of US. Serial No. 08/412,810 filed March 29, 1995; which is a continuation-
in-part of 08/265,533 filed June 24, 1994.

FIELD OF THE INVENTION

15 This invention relates to certain monocyclopentadienyl metal
compounds, to certain catalyst systems comprising such
monocyclopentadienyl metal compounds along with an activator, and to a
process using such catalyst systems for production of polyolefins,
particularly high molecular weight ethylene- α -olefin copolymers having a
high level of α -olefin comonomer incorporation.

20

BACKGROUND OF THE INVENTION

As is well known, various processes and catalysts exist for
homopolymerization or copolymerization of olefins. For many
applications it is of primary importance for a polyolefin to have a high
25 weight average molecular weight while having a relatively narrow
molecular weight distribution. A high weight average molecular weight,
when accompanied by a narrow molecular weight distribution, provides
a polyolefin or an ethylene- α -olefin copolymer with high strength
properties.

30

US Patent Number 5,264,504 discloses certain monocyclopenta-
dienyl metal compounds having an amido radical with an aliphatic or
alicyclic hydrocarbyl moiety attached thereto through a primary or
secondary carbon atom. EPO 416,815 discloses certain monocyclopenta-
35 dienyl metal compounds which are activated with an alumoxane co-
catalyst. U.S. Patent Number 5,064,802 discloses certain monocyclopenta-

dienyl metal compounds which are activated with a non-coordinating compatible anion of a Bronsted acid salt.

SUMMARY OF THE INVENTION


5 The present invention is directed to certain monocyclopentadienyl compounds and to catalyst systems which include such monocyclopentadienyl metal compounds along with an activator component. The catalyst systems of the present invention are highly productive for polymerizing ethylene and olefins to produce high molecular weight
10 copolymers having a high content of α -olefin comonomer. More particularly, the present invention relates to certain monocyclopentadienyl metal compounds which include an amido moiety having an alicyclic hydrocarbyl moiety covalently bonded thereto through a tertiary carbon atom. A tertiary carbon atom is defined here as
15 a carbon atom bonded to three other non-hydrogen atoms.

DETAILED DESCRIPTION OF THE INVENTION

 This invention relates to the discovery of certain monocyclopentadienyl metal compounds which, by reason of the presence therein of
20 ligands of a particular nature, are particularly useful in catalyst systems to provide greatly improved performance characteristics. The monocyclopentadienyl metal compounds of the present invention are represented by the formula:

25

Formula I



wherein: M is Zr, Hf or Ti;

30 (C₅H_{4-x}R_x) is a cyclopentadienyl ring which is substituted with from zero to four substituent groups R, "x" is 0, 1, 2, 3, or 4 denoting the degree of substitution, and each substituent group R is, independently, a

radical selected from C₁-C₂₀ hydrocarbyl radicals, substituted C₁-C₂₀ hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical, an aryloxy radical or any other radical containing a Lewis acidic or basic functionality; C₁-C₂₀ hydrocarbyl-substituted metalloid radicals wherein the metalloid is selected from the Group IV A of the Periodic Table of Elements; halogen radicals; amido radicals; phosphido radicals; alkoxy radicals; alkylborido radicals; or any other radical containing Lewis acidic or basic functionality; or (C₅H_{4-x}R_x) is a cyclopentadienyl ring in which at least two adjacent R-groups are joined together and along with the carbon atoms to which they are attached form a C₄-C₂₀ ring system;

R' is a radical selected from C₄-C₃₀, preferably C₄-C₂₀, alicyclic hydrocarbyl radicals wherein one or more hydrogen atoms may be replaced by radicals containing Lewis acidic or basic functionalities such as, for example, radicals selected from halogen, amido, phosphido, alkoxy, aryloxy and the like, with the proviso that R' is covalently bonded to the nitrogen atom through a tertiary carbon atom;

each Q is independently a radical selected from halide; hydride; substituted or unsubstituted C₁-C₂₀ hydrocarbyl; alkoxide; aryloxy; amide; or phosphide; or both Q together may be an alkylidene or a cyclometallated hydrocarbyl or any other divalent anionic chelating ligand, with the proviso that where any Q is a hydrocarbyl radical, such Q is not a substituted or unsubstituted cyclopentadienyl radical;

T is a covalent bridging group containing a Group IV A or V A element such as, but not limited to, a dialkyl, dialicycyl, alkylalicycyl, arylalicycyl, alkylaryl or diaryl silicon or germanium radical; alkyl and/or aryl phosphine or amine radical; or a substituted or unsubstituted hydrocarbyl radical such as methylene, ethylene and the like which may be substituted with substituents selected from alkyl, alicycyl and aryl radicals or combinations thereof having from 1 to 20 carbon atoms and silyl atoms.


Such compounds can also include an L_w complexed thereto wherein L is a neutral Lewis base. Examples of such neutral Lewis bases include but are not limited to diethylether, tetraethylammonium chloride, tetrahydrofuran, dimethylaniline, aniline, trimethylphosphine, n-

butylamine, and the like. The "w" is a number from 0 to 3. Optionally, L may be covalently bonded to one or both Q provided Q is not hydride or halide.

- L can also be a second transition metal compound of the same type
 5 such that the two metal centers M and M' are bridged by Q and Q', wherein M' has the same meaning as M, and Q' has the same meaning as Q. Such dimeric compounds are represented by the formula:

Formula II


10



A preferred class of compounds of the present invention are represented by the formula:

15

Formula III



20 wherein:

M is selected from Ti, Hf and Zr;

(C₅H_{4-x}R_x) is as defined above with respect to Formula I;

each of R¹ and R² are independently selected from C₁-C₂₀

hydrocarbyl radicals, and may optionally be joined together to form a

25 cyclic ring structure;

T is Si or Ge;


each Q is independently selected from halide, hydride, substituted or unsubstituted C₁-C₂₀ hydrocarbyl radicals; alkoxide; amide; and phosphide radicals, with the proviso that Q is not a substituted or unsubstituted cyclopentadienyl radical;

- 5 R^1 is selected from C₄-C₂₀ alicyclic hydrocarbyl radicals with the proviso that R^1 is covalently bonded to the nitrogen atom through a tertiary carbon atom; and

L_w is optional and is as defined above.

- A more preferred class of compounds of the present invention are
10 those compounds represented by Formula IV:

Formula IV



15

wherein:

M is selected from Ti, Zr and Hf;

Ti is selected from Si or Ge;

- each of R^1 and R^2 is independently selected from C₁-C₂₀ alkyl, C₆-C₂₂ aryl, C₃-C₂₀ cycloalkyl radicals or combinations thereof and may
20 optionally be joined together to form a cyclic ring structure;

each R^3 is independently selected from hydrogen; C₁-C₂₀ alkyl; C₃-C₂₀ cycloalkyl; C₆-C₂₂ aryl; halogen; amido; phosphido; alkoxy; aryloxy; alkylborido; and the like radicals; or combinations thereof;

- 25 each Q is independently selected from hydrogen; halogen; C₁-C₂₀ alkyl; C₆-C₂₂ aryl; C₃-C₂₀ cycloalkyl; alkoxy; aryloxy; amido; and phosphido radicals or combinations thereof;

u is an integer of from 0 to 6, preferably 0 to 4, such as from 1 to 3;
x is 0-4;

each R⁴ is independently selected from hydrogen; halogen, C₁-C₁₀ alkyl; C₃-C₁₀ cycloalkyl; C₆-C₂₂ aryl; amido; alkoxy; aryloxy; or
5 combinations thereof and the like radicals; or two R⁴ groups along with the carbon atom or atoms to which they are attached, form a saturated or partially saturated alicyclic group or form an aryl group; and

Lw is optional and is as defined above.

Preferred compounds within the scope of Formula IV are those
10 wherein each R³ is independently selected from C₁-C₂₀ alkyl; C₃-C₂₀ cycloalkyl; C₆-C₂₂ aryl; or combinations thereof; and M is titanium. As utilized herein, the term "alkyl", alone or in combination, means a straight-chain or branched-chain alkyl radical containing from 1 to about 20, preferably from 1 to about 10 carbon atoms. Examples of such radicals
15 include methyl, ethyl, n-propyl, iso-propyl, n-butyl, iso-butyl, sec-butyl, tert-butyl, pentyl, iso-amyl, hexyl, octyl, decyl, dodecyl, and the like. Such alkyl and alicyclic radicals may carry one or more substitutes selected from alkoxy, halo, aryloxy, hydroxy, amino, phosphino, borido, nitro and the like. The term "alkoxy", alone or in combination means an
20 alkyl oxy radical wherein the term "alkyl" is as defined above. Examples of suitable alkoxy radicals include methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, sec-butoxy, tert-butoxy, pentoxy and the like. The term "alicyclic", alone or in combination, means a branched or unbranched cyclic alkyl radical as defined above which is saturated, or
25 partially saturated. Examples of such alicyclic radicals include cyclopropyl, cyclobutyl, cyclohexyl, cyclododecyl, 2-methylcyclohexyl, norbornyl, adamantyl and the like. The term "aryl", alone or in combination, means a mono, bi or poly aromatic radical. Examples of such radicals include phenyl, cycloheptatrienyl, naphthyl, anthracenyl, chrysenyl, azulenyl, biphenyl, p-terphenyl, 1-phenyl naphethyl and the
30 like. Such aryl radicals may carry one or more substituents selected from alkyl, alkoxy, aryloxy, halogen, hydroxy, amino, phosphido, borido, nitro and the like. Examples of such substituted aryl radicals include p-tolyl, 4-methoxyphenyl, 4-t-butylphenyl and the like. The term "aryloxy", alone
35 or in combination, means an aryl oxy radical wherein aryl is as defined above. Examples include phenoxy and the like. The term "halogen" or

"halo" means fluoride, chloride, bromide or iodide radicals. The term "ring system" means a bi- or polycyclic system wherein one or more aromatic radicals is fused to one or more alicyclic and/or aryl radicals. Examples of such ring systems include fluorenyl, indenyl,

5 tetrahydroindenyl, benzindenyl, and the like which systems may be substituted with one or more radicals such as alkyl radicals.

A tertiary (3°) carbon atom means a carbon atom which is bonded to three other non-hydrogen atoms. An alicyclic hydrocarbyl radical bonded to a nitrogen atom through a tertiary carbon atom means that the
10 tertiary carbon atom is a member of the alicyclic radical and is bonded to three other non-hydrogen atoms, such as to three carbon atoms. Examples of such radicals include 1-adamantyl, 3-noradamantyl, 1-norbornyl, 1-triptyceny, 1-tricyclo[5.2.1.0^{2,6}]decyl, 4-tricyclo[2.2.1.0^{2,6}]heptyl, and the like. The term "hydrocarbyl" means a
15 radical derived from a hydrocarbon. Preferred hydrocarbyl radicals are those containing from 1-20 carbon atoms. Examples of such radicals include alkyl, aryl, cycloalkyl radicals or combinations thereof. Preferred radicals are C₁-C₂₀ alkyl, C₆-C₂₂ aryl, and C₃-C₂₀ cycloalkyl radicals, or combinations thereof.

20 A more preferred class of compounds are those compounds represented by the above Formula IV wherein M is Ti. A most preferred class of compounds are those represented by the above Formula IV wherein M is Ti and wherein R₁ and R₂ are independently selected from C₁-C₆ alkyl radicals, C₆-C₁₂ aryl radicals, C₃-C₁₂ cycloalkyl radicals, and
25 combinations thereof.

Examples of specific compounds within the classes of compounds defined by Formula IV include:

dimethylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
30 dimethylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantylamido)titanium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
35 (3-fluoro-1-adamantylamido)titanium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-

(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantyl)titanium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
5 (3,5,7-trimethyladamantyl)titanium dimethyl;

methylphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
10 (3-noradamantylamido)titanium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-adamantylamido)titanium dimethyl
15 methylphenylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyladamantylamido)titanium dimethyl
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
20 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

diphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
25 (3-noradamantylamido)titanium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
30 diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5,7 trimethyl-1-adamantylamido)titanium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
35 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

- dimethylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)titanium diphenyl;
5 dimethylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
10 (3,5,7-trimethyl-1-adamantylamido)titanium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium diphenyl;
15 methylphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)titanium diphenyl;
20 methylphenylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
25 (3,5,7-trimethyl-1-adamantylamido)titanium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium diphenyl;
30 diphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium diphenyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)titanium diphenyl;
35 diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium diphenyl;

- diphenylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium diphenyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium diphenyl;
5 diphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium diphenyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium diphenyl;
- 10 dimethylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)hafnium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
15 (3,5-dimethyl-1-adamantylamido)hafnium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)hafnium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)hafnium dimethyl;
20 dimethylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium dimethyl;
- 25 methylphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)hafnium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
30 (3,5-dimethyl-1-adamantylamido)hafnium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)hafnium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)hafnium dimethyl;
35 methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium dimethyl;

methylphenylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium dimethyl;

5 diphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)hafnium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
10 (3,5-dimethyl-1-adamantylamido)hafnium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)hafnium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)hafnium dimethyl;
15 diphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium dimethyl;

20 dimethylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)hafnium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)hafnium diphenyl;
25 dimethylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)hafnium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)hafnium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
30 (3-fluoro-1-adamantylamido)hafnium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium diphenyl;

35 methylphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-

(3-noradamantanylamido)hafnium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)hafnium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
5 (3-methyl-1-adamantylamido)hafnium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)hafnium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium diphenyl;
10 methylphenylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium diphenyl;

diphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium diphenyl;
15 diphenylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)hafnium diphenyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)hafnium diphenyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
20 (3-methyl-1-adamantylamido)hafnium diphenyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)hafnium diphenyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium diphenyl;
25 diphenylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium diphenyl;

dimethylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium dimethyl;
30 dimethylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)zirconium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)zirconium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
35 (3-methyl-1-adamantylamido)zirconium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-

(3,5,7-trimethyl-1-adamantylamido)zirconium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)zirconium dimethyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
5 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium dimethyl;

methylphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
10 (3-noradamantanylamido)zirconium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)zirconium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)zirconium dimethyl;
15 methylphenylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)zirconium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)zirconium dimethyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
20 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium dimethyl;

diphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
25 (3-noradamantanylamido)zirconium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)zirconium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)zirconium dimethyl;
30 diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)zirconium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)zirconium dimethyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
35 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium dimethyl;

- dimethylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)zirconium diphenyl;
5 dimethylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)zirconium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)zirconium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
10 (3,5,7-trimethyl-1-adamantylamido)zirconium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)zirconium diphenyl;
dimethylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium diphenyl;
15 methylphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)zirconium diphenyl;
20 methylphenylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)zirconium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)zirconium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
25 (3,5,7-trimethyl-1-adamantylamido)zirconium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)zirconium diphenyl;
methylphenylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium diphenyl;
30 diphenylsilyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium diphenyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)zirconium diphenyl;
35 diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)zirconium diphenyl;

- diphenylsilyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)zirconium diphenyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)zirconium diphenyl;
5 diphenylsilyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)zirconium diphenyl;
diphenylsilyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium diphenyl;
- 10 dimethylgermanyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(3-noradamantylamido)titanium dimethyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
15 (3,5-dimethyl-1-adamantylamido)titanium dimethyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
20 dimethylgermanyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;
- 25 methylphenylgermanyl(tetramethylcyclopentadienyl)-
(1-adamantylamido) titanium dimethyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3-noradamantylamido)titanium dimethyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
30 (3,5-dimethyl-1-adamantylamido)titanium dimethyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
35 methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;

methylphenylgermany(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

5 diphenylgermany(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
diphenylgermany(tetramethylcyclopentadienyl)-
(3-noradamantylamido)titanium dimethyl;
diphenylgermany(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
10 diphenylgermany(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
diphenylgermany(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
diphenylgermany(tetramethylcyclopentadienyl)-
15 (3-fluoro-1-adamantylamido)titanium dimethyl;
diphenylgermany(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

20 dimethylgermany(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium diphenyl;
dimethylgermany(tetramethylcyclopentadienyl)-
(3-noradamantylamido)titanium diphenyl;
dimethylgermany(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium diphenyl;
25 dimethylgermany(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium diphenyl;
dimethylgermany(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium diphenyl;
dimethylgermany(tetramethylcyclopentadienyl)-
30 (3-fluoro-1-adamantylamido)titanium diphenyl;
dimethylgermany(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium diphenyl;

35 methylphenylgermany(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium diphenyl;
methylphenylgermany(tetramethylcyclopentadienyl)-

- (3-noradamantanylamido)titanium diphenyl;
methylphenylgermany(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium diphenyl;
methylphenylgermany(tetramethylcyclopentadienyl)-
5 (3-methyl-1-adamantylamido)titanium diphenyl;
methylphenylgermany(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium diphenyl;
methylphenylgermany(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium diphenyl;
10 methylphenylgermany(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium diphenyl;
- diphenylgermany(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium diphenyl;
15 diphenylgermany(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)titanium diphenyl;
diphenylgermany(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium diphenyl;
diphenylgermany(tetramethylcyclopentadienyl)-
20 (3-methyl-1-adamantylamido)titanium diphenyl;
diphenylgermany(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium diphenyl;
diphenylgermany(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium diphenyl;
25 diphenylgermany(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium diphenyl;
- dimethylgermany(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium dimethyl;
30 dimethylgermany(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)hafnium dimethyl;
dimethylgermany(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)hafnium dimethyl;
dimethylgermany(tetramethylcyclopentadienyl)-
35 (3-methyl-1-adamantylamido)hafnium dimethyl;
dimethylgermany(tetramethylcyclopentadienyl)-

(3,5,7-trimethyl-1-adamantylamido)hafnium dimethyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium dimethyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
5 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium diphenyl;

methylphenylgermanyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium dimethyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
10 (3-noradamantylamido)hafnium dimethyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)hafnium dimethyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)hafnium dimethyl;
15 methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)hafnium dimethyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium dimethyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
20 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium dimethyl;

diphenylgermanyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium dimethyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
25 (3-noradamantylamido)hafnium dimethyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)hafnium dimethyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)hafnium dimethyl;
30 diphenylgermanyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)hafnium dimethyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium dimethyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
35 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium dimethyl;

- dimethylgermanyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium diphenyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)hafnium diphenyl;
5 dimethylgermanyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)hafnium diphenyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)hafnium diphenyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
10 (3,5,7-trimethyl-1-adamantylamido)hafnium diphenyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium diphenyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium diphenyl;
15 methylphenylgermanyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium diphenyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)hafnium diphenyl;
20 methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)hafnium diphenyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)hafnium diphenyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
25 (3,5,7-trimethyl-1-adamantylamido)hafnium diphenyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium diphenyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium diphenyl;
30 diphenylgermanyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)hafnium diphenyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)hafnium diphenyl;
35 diphenylgermanyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)hafnium diphenyl;

- diphenylgermany(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)hafnium diphenyl;
diphenylgermany(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)hafnium diphenyl;
5 diphenylgermany(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)hafnium diphenyl;
diphenylgermany(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)hafnium diphenyl;
- 10 dimethylgermany(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium dimethyl;
dimethylgermany(tetramethylcyclopentadienyl)-
(3-noradamantylamido)zirconium dimethyl;
dimethylgermany(tetramethylcyclopentadienyl)-
15 (3,5-dimethyl-1-adamantylamido)zirconium dimethyl;
dimethylgermany(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)zirconium dimethyl;
dimethylgermany(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)zirconium dimethyl;
20 dimethylgermany(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)zirconium dimethyl;
dimethylgermany(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium dimethyl;
- 25 methylphenylgermany(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium dimethyl;
methylphenylgermany(tetramethylcyclopentadienyl)-
(3-noradamantylamido)zirconium dimethyl;
methylphenylgermany(tetramethylcyclopentadienyl)-
30 (3,5-dimethyl-1-adamantylamido)zirconium dimethyl;
methylphenylgermany(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)zirconium dimethyl;
methylphenylgermany(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)zirconium dimethyl;
35 methylphenylgermany(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)zirconium dimethyl;

methylphenylgermanyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium dimethyl;

5 diphenylgermanyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium dimethyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
(3-noradamantylamido)zirconium dimethyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)zirconium dimethyl;
10 diphenylgermanyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)zirconium dimethyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)zirconium dimethyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
15 (3-fluoro-1-adamantylamido)zirconium dimethyl;
diphenylgermanyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium dimethyl;

20 dimethylgermanyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium diphenyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(3-noradamantylamido)zirconium diphenyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)zirconium diphenyl;
25 dimethylgermanyl(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)zirconium diphenyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)zirconium diphenyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
30 (3-fluoro-1-adamantylamido)zirconium diphenyl;
dimethylgermanyl(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium diphenyl;

35 methylphenylgermanyl(tetramethylcyclopentadienyl)-
(1-adamantylamido)zirconium diphenyl;
methylphenylgermanyl(tetramethylcyclopentadienyl)-

(3-noradamantanylamido)zirconium diphenyl;
 methylphenylgermanyl(tetramethylcyclopentadienyl)-
 (3,5-dimethyl-1-adamantylamido)zirconium diphenyl;
 methylphenylgermanyl(tetramethylcyclopentadienyl)-
 5 (3-methyl-1-adamantylamido)zirconium diphenyl;
 methylphenylgermanyl(tetramethylcyclopentadienyl)-
 (3,5,7-trimethyl-1-adamantylamido)zirconium diphenyl;
 methylphenylgermanyl(tetramethylcyclopentadienyl)-
 (3-fluoro-1-adamantylamido)zirconium diphenyl;
 10 methylphenylgermanyl(tetramethylcyclopentadienyl)-
 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium diphenyl;

diphenylgermanyl(tetramethylcyclopentadienyl)-
 (1-adamantylamido)zirconium diphenyl;
 15 diphenylgermanyl(tetramethylcyclopentadienyl)-
 (3-noradamantanylamido)zirconium diphenyl;
 diphenylgermanyl(tetramethylcyclopentadienyl)-
 (3,5-dimethyl-1-adamantylamido)zirconium diphenyl;
 diphenylgermanyl(tetramethylcyclopentadienyl)-
 20 (3-methyl-1-adamantylamido)zirconium diphenyl;
 diphenylgermanyl(tetramethylcyclopentadienyl)-
 (3,5,7-trimethyl-1-adamantylamido)zirconium diphenyl;
 diphenylgermanyl(tetramethylcyclopentadienyl)-
 (3-fluoro-1-adamantylamido)zirconium diphenyl;
 25 diphenylgermanyl(tetramethylcyclopentadienyl)-
 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)zirconium diphenyl;


The above specific examples wherein each Q is methyl or each Q is
 phenyl is prepared from the corresponding compound wherein each Q is
 30 chloro. The dichloro (both Q are Cl) species of each of the above
 compounds are also within Formula II.

Another preferred class of compounds of the present invention are
 those compounds represented by the formula:

35

Formula V

23



wherein R^3 , R^4 , Q , M , u , w , x , and L are as defined above;

wherein T is selected from radicals of the formula $(CR^5R^6)_y$ wherein R^5 and R^6 are independently selected from hydrogen and C_1 - C_{20} hydrocarbyl radicals; and wherein y is 1, 2, or 3.

A more preferred class of compounds are those compounds represented by the above Formula V wherein M is Ti. A most preferred class of compounds are those represented by the above Formula V wherein M is Ti and wherein R^5 and R^6 are independently selected from hydrogen, C_1 - C_6 alkyl radicals, C_6 - C_{12} aryl radicals, C_3 - C_{12} cycloalkyl radicals and combinations thereof.

Examples of specific compounds within the class of compounds defined by Formula V include:

- methylene(tetramethylcyclopentadienyl)-(1-adamantylamido)titanium dimethyl;
- methylene(tetramethylcyclopentadienyl)-(3-noradamantylamido)titanium dimethyl;
- methylene(tetramethylcyclopentadienyl)-(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
- methylene(tetramethylcyclopentadienyl)-(3-methyl-1-adamantylamido)titanium dimethyl;
- methylene(tetramethylcyclopentadienyl)-(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
- methylene(tetramethylcyclopentadienyl)-(3-fluoro-1-adamantylamido)titanium dimethyl;

methylene(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

5 dimethylmethylene(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
dimethylmethylene(tetramethylcyclopentadienyl)-
(3-noradamantylamido)titanium dimethyl;
dimethylmethylene(tetramethylcyclopentadienyl)-
10 (3,5-dimethyl-1-adamantylamido)titanium dimethyl;
dimethylmethylene(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
dimethylmethylene(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
15 dimethylmethylene(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
dimethylmethylene(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

20 diethylmethylene(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
diethylmethylene(tetramethylcyclopentadienyl)-
(3-noradamantylamido)titanium dimethyl;
diethylmethylene(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
25 diethylmethylene(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
diethylmethylene(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
diethylmethylene(tetramethylcyclopentadienyl)-
30 (3-fluoro-1-adamantylamido)titanium dimethyl;
diethylmethylene(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

35 ethylene(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
ethylene(tetramethylcyclopentadienyl)-

- (3-noradamantanylamido)titanium dimethyl;
ethylene(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
ethylene(tetramethylcyclopentadienyl)-
5 (3-methyl-1-adamantylamido)titanium dimethyl;
ethylene(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
ethylene(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
10 ethylene(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;
- 1,1-dimethylethylene(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
15 1,1-dimethylethylene(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)titanium dimethyl;
1,1-dimethylethylene(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
1,1-dimethylethylene(tetramethylcyclopentadienyl)-
20 (3-methyl-1-adamantylamido)titanium dimethyl;
1,1-dimethylethylene(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
1,1-dimethylethylene(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
25 1,1-dimethylethylene(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;
- 1,1-dipropylethylene(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
30 1,1-dipropylethylene(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)titanium dimethyl;
1,1-dipropylethylene(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
1,1-dipropylethylene(tetramethylcyclopentadienyl)-
35 (3-methyl-1-adamantylamido)titanium dimethyl;
1,1-dipropylethylene(tetramethylcyclopentadienyl)-

(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
1,1-dipropylethylene(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
1,1-dipropylethylene(tetramethylcyclopentadienyl)-
5 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

1,2-dimethylethylene(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
1,2-dimethylethylene(tetramethylcyclopentadienyl)-
10 (3-noradamantylamido)titanium dimethyl;
1,2-dimethylethylene(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
1,2-dimethylethylene(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
15 1,2-dimethylethylene(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
1,2-dimethylethylene(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
1,2-dimethylethylene(tetramethylcyclopentadienyl)-
20 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

1,2-dipropylethylene(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
1,2-dipropylethylene(tetramethylcyclopentadienyl)-
25 (3-noradamantylamido)titanium dimethyl;
1,2-dipropylethylene(tetramethylcyclopentadienyl)-
(3,5-dimethyl-1-adamantylamido)titanium dimethyl;
1,2-dipropylethylene(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
30 1,2-dipropylethylene(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
1,2-dipropylethylene(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
1,2-dipropylethylene(tetramethylcyclopentadienyl)-
35 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

- 2,2-dimethylethylen (tetramethylcyclopentadienyl)-
 (1-adamantylamido)titanium dimethyl;
 2,2-dimethylethylene(tetramethylcyclopentadienyl)-
 (3-noradamantanylamido)titanium dimethyl;
 5 2,2-dimethylethylene(tetramethylcyclopentadienyl)-
 (3,5-dimethyl-1-adamantylamido)titanium dimethyl;
 2,2-dimethylethylene(tetramethylcyclopentadienyl)-
 (3-methyl-1-adamantylamido)titanium dimethyl;
 2,2-dimethylethylene(tetramethylcyclopentadienyl)-
 10 (3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
 2,2-dimethylethylene(tetramethylcyclopentadienyl)-
 (3-fluoro-1-adamantylamido)titanium dimethyl;
 2,2-dimethylethylene(tetramethylcyclopentadienyl)-
 (4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;
 15 2,2-dipropylethylene(tetramethylcyclopentadienyl)-
 (1-adamantylamido)titanium dimethyl;
 2,2-dipropylethylene(tetramethylcyclopentadienyl)-
 (3-noradamantanylamido)titanium dimethyl;
 20 2,2-dipropylethylene(tetramethylcyclopentadienyl)-
 (3,5-dimethyl-1-adamantylamido)titanium dimethyl;
 2,2-dipropylethylene(tetramethylcyclopentadienyl)-
 (3-methyl-1-adamantylamido)titanium dimethyl;
 2,2-dipropylethylene(tetramethylcyclopentadienyl)-
 25 (3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
 2,2-dipropylethylene(tetramethylcyclopentadienyl)-
 (3-fluoro-1-adamantylamido)titanium dimethyl;
 2,2-dipropylethylene(tetramethylcyclopentadienyl)-
 (4-tricyclo[2.2.1.0^{2,6}]heptylmido)titanium dimethyl;
 30 1,1-diphenylethylene(tetramethylcyclopentadienyl)-
 (1-adamantylamido)titanium dimethyl;
 1,1-diphenylethylene(tetramethylcyclopentadienyl)-
 (3-noradamantanylamido)titanium dimethyl;
 35 1,1-diphenylethylene(tetramethylcyclopentadienyl)-
 (3,5-dimethyl-1-adamantylamido)titanium dimethyl;

- 1,1-diphenylethylene(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
1,1-diphenylethylene(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
5 1,1-diphenylethylene(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
1,1-diphenylethylene(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;
- 10 1,2-diphenylethylene(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
1,2-diphenylethylene(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)titanium dimethyl;
1,2-diphenylethylene(tetramethylcyclopentadienyl)-
15 (3,5-dimethyl-1-adamantylamido)titanium dimethyl;
1,2-diphenylethylene(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
1,2-diphenylethylene(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
20 1,2-diphenylethylene(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;
1,2-diphenylethylene(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;
- 25 2,2-diphenylethylene(tetramethylcyclopentadienyl)-
(1-adamantylamido)titanium dimethyl;
2,2-diphenylethylene(tetramethylcyclopentadienyl)-
(3-noradamantanylamido)titanium dimethyl;
2,2-diphenylethylene(tetramethylcyclopentadienyl)-
30 (3,5-dimethyl-1-adamantylamido)titanium dimethyl;
2,2-diphenylethylene(tetramethylcyclopentadienyl)-
(3-methyl-1-adamantylamido)titanium dimethyl;
2,2-diphenylethylene(tetramethylcyclopentadienyl)-
(3,5,7-trimethyl-1-adamantylamido)titanium dimethyl;
35 2,2-diphenylethylene(tetramethylcyclopentadienyl)-
(3-fluoro-1-adamantylamido)titanium dimethyl;

2,2-diphenylethylene(tetramethylcyclopentadienyl)-
(4-tricyclo[2.2.1.0^{2,6}]heptylamido)titanium dimethyl;

The above named specific compounds wherein each Q is methyl
5 are prepared from the corresponding compound wherein each Q is
chloro. Thus, specific compounds within Formula V are those wherein
each Q is chloro. Also, the corresponding compounds wherein each Q is
phenyl, and M is zirconium or hafnium in place of titanium and (CR³R⁴)_y
is methylphenylmethylene, tetramethylethylene, tetraethylethylene,
10 propylene, hexamethylpropylene, 1,1-dimethyl propylene, 1,1,2,2-
tetramethylpropylene and the like, are also specific compounds within the
above Formula V.

The compounds of the present invention can be made using the
following general procedure and the specific examples set forth herein.

15 A lithiated monocyclopentadienyl compound (C₅H_{5-x}R_x)Li is
reacted with a dihalide of a bridging compound, R¹R²TX₂ wherein X is a
halide radical, in a suitable solvent such as tetrahydrofuran. The
resulting compound is represented by the formula (C₅H_{5-x}R_x)TR¹R²X.

The compound (C₅H_{5-x}R_x)TR¹R²X is then reacted with a lithiated
20 amido compound of the formula LiHN-R' in a suitable solvent followed
by addition of two equivalents of methyl lithium or similar compound,
and subsequent addition of a Group IV metal compound complex such as
MX₄·2Et₂O wherein M is a metal and X is a halide. The resulting
compound is represented by the formula R¹R²T(C₅H_{4-x}R_x)(N-R')MX₂.

25 The compound R¹R²T(C₅H_{4-x}R_x)(N-R')MX₂ can be utilized as is
or it can be converted to the corresponding dihydride, dialkyl, diaryl
dicycloalkyl, dialkylaryl, dicycloalkylaryl, dialkylcycloalkyl, or mixtures
thereof and the like to utilize with an activator which is not suitable for
use when the Q ligands are halide and the like as more fully set forth
30 below.

Monocyclopentadienyl metal compounds of the present invention
have been discovered to produce a highly productive catalyst system
which produces an ethylene- α -olefin copolymer of significantly greater
molecular weight and α -olefin comonomer content as compared with
35 other species of monocyclopentadienyl metal compounds when utilized

in an otherwise identical catalyst system under identical polymerization conditions.

All of the above-defined monocyclopentadienyl metal compounds are useful, in combination with an activator or co-catalyst, to polymerize α -olefins or other unsaturated hydrocarbon based monomers including cyclic olefins. Suitable activators include alumoxanes and activators comprising a cation and a non-coordinating compatible anion.

The alumoxane component is an oligomeric compound which may be represented by the general formula $(R^{10}-Al-O)_m$ which is a cyclic compound, or may be $R^{11}(R^{12}Al-O)_mAlR^{13}_2$ which is a linear compound. An alumoxane is generally a mixture of both the linear and cyclic compounds. In the general alumoxane formula R^{10} , R^{11} , R^{12} and R^{13} are, independently a C_1 - C_5 alkyl radical, for example, methyl, ethyl, propyl, butyl or pentyl and "m" is an integer from 1 to about 50. Most preferably, R^{10} , R^{11} , R^{12} and R^{13} are each methyl and "m" is at least 4. When an alkyl aluminum halide is employed in the preparation of the alumoxane, one or more R^{10-13} groups may be halide.


As is now well known, alumoxanes can be prepared by various procedures. For example, a trialkyl aluminum may be reacted with water, in the form of a moist inert organic solvent; or the trialkyl aluminum may be contacted with a hydrated salt, such as hydrated copper sulfate suspended in an inert organic solvent, to yield an alumoxane. Generally, however prepared, the reaction of a trialkyl aluminum with a limited amount of water yields a mixture of both linear and cyclic species of alumoxane.

Suitable alumoxanes utilized in the catalyst systems of this invention are those prepared by the hydrolysis of a trialkylaluminum; such as trimethylaluminum, triethylaluminum, tripropylaluminum; triisobutylaluminum, dimethylaluminumchloride, diisobutylaluminumchloride, diethylaluminumchloride, and the like. The most preferred alumoxane for use is methylalumoxane (MAO). Methylalumoxanes having an average degree of oligomerization of from about 4 to about 25 ("m" = 4 to 25), with a range of 13 to 25, are the most preferred.

Modified alumoxanes can also be utilized. Examples of such modified alumoxanes are those disclosed in U. S. 5,041,584; EP 0 516 476; and EP 0 561 476 which are incorporated herein by reference.

Activators comprising a non-coordinating compatible anion component are described in U.S. Patent No. 5,198,401 which is incorporated herein by reference. Compounds useful as the activator compound, in the preparation of the catalyst comprise a cation, preferably a Bronsted acid capable of donating a proton, and a compatible non-coordinating anion containing a single coordination complex comprising a charge-bearing metal or metalloid core which is relatively large (bulky), capable of stabilizing the active catalyst species (the Group IV-B cation) which is formed when the metallocene and activator compounds are combined, and said anion is sufficiently labile to be displaced by olefinic, diolefinic and acetylenically unsaturated substrates or other neutral Lewis bases such as ethers, nitriles and the like. It is well known that reactive cations other than Bronsted acids capable of donating a proton are also useful. Examples of such other cations include ferrocenium triphenylcarbonium and triethylsilylium cations. Any metal or metalloid capable of forming a coordination complex which is resistant to degradation by water (or other Bronsted or Lewis Acids) may be used or contained in the anion of the second activator compound. Suitable metals include, but are not limited to, aluminum, gold, platinum and the like. Suitable metalloids include, but are not limited to, boron, phosphorus, silicon and the like.

Compounds containing anions which comprise coordination complexes containing a single metal or metalloid atom are, of course, well known and many, particularly compounds containing a single boron atom in the anion portion, are available commercially. See, for example, U. S. Patent No. 5,278,119. In light of this, salts containing anions comprising a coordination complex containing a single boron atom are preferred. In general, the second activator compounds useful in the preparation of the catalysts of this invention may be represented by the following general formula:



wherein:

L' is a neutral Lewis base;

H is a hydrogen atom;

[L'-H] is a Bronsted acid;

5 M' is a metal or metalloid;

Q^m₁ to Q^m_n are, independently, hydride radicals, bridged or unbridged dialkylamido radicals, alkoxide and aryloxy radicals, hydrocarbyl and substituted hydrocarbyl radicals, halocarbyl and substituted halocarbyl radicals, and hydrocarbyl- and halocarbyl-substituted organometalloid radicals and any one, but not more than one, of Q₁ to Q_n may be a halide radical;

m is an integer representing the formal valence charge of M';

n is the total number of ligands Q; and

15 d is an integer representing the total charge on the anion.

Activator compounds comprising boron which are particularly useful in the preparation of catalysts of this invention are represented by the following general formula:



20 wherein:

L' is a neutral Lewis base;

H is a hydrogen atom;

[L'-H]⁺ is a Bronsted acid;

B is boron in a valence state of 3⁺;

25 Ar₁ and Ar₂ are the same or different substituted-aromatic hydrocarbon radicals and may be linked to each other through a stable bridging group; and

X₃ and X₄ are, independently, hydride radicals, halide radicals, with the proviso that only X₃ or X₄ will be halide, hydrocarbyl radicals, substituted-hydrocarbyl radicals, halocarbyl radicals, substituted-halocarbyl radicals, hydrocarbyl- and halocarbyl-substituted organometalloid radicals, dialkylamido radicals, and alkoxy and aryloxy radicals.

35 In general, Ar₁ and Ar₂ may, independently, be any aromatic or substituted-aromatic hydrocarbon radical. Suitable aromatic radicals

include, but are not limited to, phenyl, naphthyl and anthracenyl radicals. Suitable substituents on useful substituted-aromatic hydrocarbon radicals, include, but are not necessarily limited to, hydrocarbyl radicals, organometalloid radicals, alkoxy radicals, alkylamido radicals, fluoro and fluorohydrocarbyl radicals and the like such as those useful as X_3 or X_4 . The substituent may be ortho, meta or para, relative to the carbon atom bonded to the boron atom. When either or both X_3 and X_4 are a hydrocarbyl radical, each may be the same or a different aromatic or substituted-aromatic radical as are Ar_1 and Ar_2 , or the same may be a straight or branched alkyl, alkenyl or alkynyl radical, a cyclic hydrocarbon radical or an alkyl-substituted cyclic hydrocarbon radical. X_3 and X_4 may also, independently, be alkoxy or dialkylamido radicals, hydrocarbyl radicals and organometalloid radicals and the like. As indicated supra, Ar_1 and Ar_2 may be linked to each other. Similarly, either or both of Ar_1 and Ar_2 could be linked to either X_3 or X_4 . Finally, X_3 and X_4 may also be linked to each other through a suitable bridging group.

Illustrative, but not limiting, examples of boron compounds which may be used as an activator component in the preparation of the improved catalysts of this invention are trialkyl-substituted ammonium salts such as triethylammonium tetra(phenyl)boron, tripropylammonium tetra(phenyl)boron, tri(n-butyl)ammonium tetra(phenyl)boron, trimethylammonium tetra(p-tolyl)boron, trimethylammonium tetra(octolyl)boron, tributylammonium tetra(pentafluorophenyl)boron, tripropylammonium tetra(o,p-dimethylphenyl)boron, tributylammonium tetra(m,m-dimethylphenyl)boron, tributylammonium tetra(p-trifluoromethylphenyl)boron, tributylammonium tetra(pentafluorophenyl)boron, tri(n-butyl)ammonium tetra(o-tolyl)boron and the like; N,N-dialkyl anilinium salts such as N,N-dimethylanilinium tetra(phenyl)boron, N,N-diethylanilinium tetra(phenyl)boron, N,N-2,4,6-pentamethylanilinium tetra(phenyl)boron and the like; dialkyl ammonium salts such as di(isopropyl)ammonium tetra(pentafluorophenyl)boron, dicyclohexylammonium tetra(phenyl)boron, and the like; and triaryl phosphonium salts such as triphenylphosphonium tetra(phenyl)boron,

tri(methylphenyl)phosphonium tetra(phenyl)boron,
tri(dimethylphenyl)phosphonium tetra(phenyl)boron and the like.

Similar lists of suitable compounds containing other metals and metalloids which are useful as activator components could be made, but such lists are not deemed necessary to a complete disclosure. In this regard, it should be noted that the foregoing list is not intended to be exhaustive and other boron compounds that would be useful as well as useful compounds containing other metals or metalloids would be readily apparent, from the foregoing general equations, to those skilled in the art.

Also useful are neutral Lewis acid ionizing activators. An example of such activator is tris(perfluorinated phenyl) boron ($B[pfp]_3$).

It is important to continued polymerization operations that either the metal cation initially formed from the metallocene, or a decomposition product thereof, be a relatively stable catalyst. It is also important that the anion of the activator compound be chemically stable and bulky. Further, when the cation of the activator component is a Bronsted acid, it is important that the acidity of the activator compound be sufficient, relative to the metallocene, to facilitate the needed proton transfer. Conversely, the basicity of the metal complex must also be sufficient to facilitate the needed proton transfer. In general, metallocenes in which the Q ligands can be hydrolyzed by aqueous solutions can be considered suitable metallocenes for forming the catalysts described herein, because water (our reference Bronsted acid) is a weaker acid than the ammonium ions used as cation in our preferred ion-exchange reagents. This concept allows one of ordinary skill in the art to choose useful metallocene components because stability to water is a basic chemical property easily determined experimentally or by using the chemical literature.


In view of the above, when utilizing an activator comprising a non-coordinating compatible anion, the metal component should be one wherein each Q is selected from the group consisting of hydride and substituted and unsubstituted hydrocarbyl radicals. Preferred Q ligands are hydride, C_1 - C_{12} alkyl and C_6 - C_{12} alkaryl and silyl radicals. Most preferred are those Q ligands selected from methyl and benzyl radicals. The preferred metal component species for use with an activator comprising a non-coordinating compatible anion are those set forth above wherein each Q is methyl. Such compounds can be generated in situ by

combining a metal component wherein Q is other than a hydride or hydrocarbyl radical with an agent, e.g., any alkylating agent, and optionally, the activator component (e.g., an alumoxane or alkyl aluminum).

5 In one embodiment of the invention, the chemical reactions which occur upon combination of a monocyclopentadienyl metal compound with a non-coordinating compatible anion activator compound may be represented by reference to the general formulae set forth herein as follows:

10


Equation I



or

15

Formula VII



wherein v is an integer $0 \leq v \leq w$

20

B' represents the anion portion of a compatible activator corresponding to the general formulae set forth in Equation I. When the monocyclopentadienyl metal compound and the non-coordinating compatible anion activator components used to prepare the improved

catalysts of the present invention are combined in a suitable solvent or diluent, all or a part of the cation of the activator (the acidic proton) combines with one of the substituents on the metallocene compound. In the case where the metallocene component has a formula corresponding to that of the general formula above, a neutral compound is liberated, which neutral compound either remains in solution or is liberated as a gas. In this regard, it should be noted that if either Q in the metallocene component is a hydride, hydrogen gas may be liberated. Similarly, if either Q is a methyl radical, methane may be liberated as a gas. In the cases where the first component wherein two Q form an alkylidene or cyclometalated hydrocarbyl diradical has a formula corresponding to those of general formulae of the reaction sequence shown directly above, the substituent on the metal is protonated but no substituent is liberated. In general, the rate of formation of the products in the foregoing reaction equations will vary depending upon the choice of the solvent, the acidity of the $[L'-H]^+$ selected, the particular L' , the anion, the temperature at which the reaction is completed and the particular monocyclopentadienyl derivative of the metal selected.

As indicated, the improved catalyst compositions of the present invention will, preferably, be prepared in a suitable solvent or diluent. Suitable solvents or diluents include any of the solvents known in the prior art to be useful as solvents in the polymerization of olefins, diolefins and acetylenically unsaturated monomers. Suitable solvents, then, include, but are not necessarily limited to, straight and branched-chain hydrocarbons such as isobutane, butane, pentane, hexane, heptane, octane and the like; cyclic and alicyclic hydrocarbons such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane and the like and, particularly aromatic and alkyl-substituted aromatic compounds such as benzene, toluene, xylene and the like. Suitable solvents also include liquid olefins which may act as monomers or comonomers including ethylene, propylene, butadiene, cyclopentene, hexene, 3-methyl-1-pentene, 4-methyl-1-pentene, 1,4-hexadiene, 1-octene, 1-decene and the like. Suitable solvents further include basic solvents which are not generally useful as polymerization solvents when conventional Ziegler-Natta type polymerization catalysts are used such as chlorobenzene.

Catalysts of this invention which are highly productive may be prepared at ratios of monocyclopentadienyl metal compound to non-coordinating compatible anion activator of 10:1 to about 1:1, preferably about 3:1 to 1:1.

- 5 With respect to the combination of a monocyclopentadienyl metal compound and non-coordinating compatible anion activator compound to form a catalyst of this invention, it should be noted that the two compounds combined for preparation of the active catalyst must be selected so as to avoid transfer of a fragment of the activator compound
- 10 anion, particularly an aryl group, to the monocyclopentadienyl metal cation, thereby forming a catalytically inactive species. When anions consisting of hydrocarbyl anions are used, there are several means of preventing anion degradation and formation of inactive species. One method is to carry out the protonolysis process in the presence of small
- 15 Lewis bases such as tetrahydrofuran. Discrete complexes can be isolated from these reactions, but the Lewis base is insufficiently labile to be displaced readily by olefin monomers, resulting in, at best, catalysts of very low activity. Another method of avoiding deleterious anion degradation is by steric hindrance. Anions of the second component
- 20 which contain aryl groups can be made more resistant to degradation by introducing substituents in the ortho positions of the phenyl rings. While active metallocene polymerization catalysts can be generated by this method, the complex reaction chemistry often prevents characterization of the catalytically active species. Steric hindrance can also result from
- 25 substitutions on the cyclopentadienyl rings of the monocyclopentadienyl metal compound component. Hence, wherein the mono(cyclopentadienyl) metal compound used is a [peralkyl-substituted monocyclopentadienyl] Group IVB metal compound, the high degree of substitution on the cyclopentadienyl ring creates sufficient bulkiness that
- 30 the Lewis base generated by the protonolysis reaction may not coordinate to the metal. Also polyarylborate anions without substituents on the aryl rings may not transfer aryl fragments to generate catalytically inactive species.

- Another means of rendering the anion of the activator compound
- 35 more resistant to degradation is afforded by fluoride substitution, especially perfluoro substitution, in the anion thereof. One class of

suitable non-coordinating anions can be represented by the formula $[B(C_6F_5)_3Q^m]$ where Q^m is a monoanionic non-bridging radical as described above. The preferred anion of the activator compound of this invention, tetra(pentafluorophenyl)boron, hereafter referred to for convenience by the notation $[B(C_6F_5)_4]$, or $[B(pfp)_4]$, is virtually impervious to degradation and can be used with a much wider range of monocyclopentadienyl metal cations, including those without substitution on the cyclopentadienyl rings, than anions comprising hydrocarbyl radicals.

Since this anion has little or no ability to coordinate to the monocyclopentadienyl metal cation and is not degraded by the monocyclopentadienyl metal cation, structures of the ion-pair catalysts using the $[B(pfp)_4]$ anion depend on steric hindrance of substituents on the cyclopentadienyl ring of the substituent on the nitrogen of the amido ligand monocyclopentadienyl metal compound, the nature of the cation of the activator component, the Lewis base liberated from the protonolysis reaction, and the ratio at which the monocyclopentadienyl metal and activator component are combined. Thus, preferred catalyst systems having a non-coordinating compatible ion activator are those compounds of the above Formulas IV-VI, and, specifically, those species set forth above, in combination with $[B(pfp)_4]$. If Lewis bases other than that liberated from the proton transfer process are present, they may complex to the metal to form modified catalysts of this invention.

Catalyst Systems

The catalyst systems employed in the method of the invention comprise a complex formed upon admixture of the metal component with an activator component. The catalyst system may be prepared by addition of the requisite metal component and either one or more alumoxane components or one or more non-coordinating anion components, or a combination of both, to an inert solvent in which olefin polymerization can be carried out by a solution, slurry or bulk phase polymerization procedure. Additional co-catalysts and/or scavenger compounds, e.g., alkyl aluminum or alkyl boron compounds, may also be included.

The catalyst system may be conveniently prepared by placing the selected metal component and the selected activator component, in any order of addition, in an alkane or aromatic hydrocarbon solvent – preferably one which is also suitable for service as a polymerization diluent. Where the hydrocarbon solvent utilized is also suitable for use as a polymerization diluent, the catalyst system may be prepared *in situ* in the polymerization reactor. Alternatively, the catalyst system may be separately prepared, in concentrated form, and added to the polymerization diluent in a reactor. Or, if desired, the components of the catalyst system may be prepared as separate solutions and added to the polymerization diluent in a reactor, in appropriate ratios, as is suitable for a continuous liquid phase polymerization reaction procedure. Alkane and aromatic hydrocarbons suitable as solvents for formation of the catalyst system and also as a polymerization diluent are exemplified by, but are not necessarily limited to, straight and branched chain hydrocarbons such as isobutane, butane, pentane, hexane, heptane, octane and the like, cyclic and alicyclic hydrocarbons such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane and the like, and aromatic and alkyl-substituted aromatic compounds such as benzene, toluene, xylene and the like. Suitable solvents also include liquid olefins which may act as monomers or comonomers including ethylene, propylene, 1-butene, 1-hexene and the like.

In accordance with this invention, when the activator is alumoxane, optimum results are generally obtained wherein the Group IV B metal compound is present in the polymerization diluent in a concentration of from about 0.0001 to about 1.0 millimoles/liter of diluent and the alumoxane component is present in an amount to provide a molar aluminum to transition metal ratio of from about 1:1 to about 20,000:1. Where the activator is one comprising a non-coordinating compatible anion and a cation, such activator is present in an amount sufficient to provide a molar ratio of metal component of from 10:1 to about 1:10. Sufficient solvent should be employed so as to provide adequate heat transfer away from the catalyst components during reaction and to permit good mixing.

The catalyst system ingredients – that is, the Group IV B metal component, the activator, and polymerization diluent – can be added to

the reaction vessel rapidly or slowly. The temperature maintained during the contact of the catalyst components can vary widely, such as, for example, from -100° to 300°C. Greater or lesser temperatures can also be employed. Preferably, during formation of the catalyst system, the
5 reaction is maintained within a temperature of from about 25° to 100°C, most preferably about 25°C.

Polymerization Process

A typical polymerization process of the invention comprises the
10 steps of contacting ethylene and a C₃-C₂₀ olefin alone, or with other unsaturated monomers including C₃-C₂₀ olefins, C₄-C₂₀ diolefins, and/or acetylenically unsaturated monomers with a catalyst comprising, in a suitable polymerization diluent, a monocyclopentadienyl metal compound, as described above, and an activator. The olefin monomers
15 include α -olefins as well as cyclic olefins such as, for example, cyclohexene, norbornene, alkyl-substituted norbornenes and the like. For example, a catalyst comprising a monocyclopentadienyl metal compound as described above and either 1) a non-coordinating compatible anion activator or 2) an alumoxane activator. The alumoxane activator is
20 utilized in an amount to provide a molar aluminum to titanium metal ratio of from about 1:1 to about 20,000:1 or more. The non-coordinating compatible anion activator is utilized in an amount to provide a molar ratio of monocyclopentadienyl metal compound to non-coordinating anion of 10:1 to about 1:10. The above reaction is conducted by reacting
25 such monomers in the presence of such catalyst system at a temperature of from about -100°C to about 300°C preferably 20°C to 250°C, most preferably from 50°C to 200°C for a time of from about 1 second to about 10 hours to produce a copolymer having a weight average molecular weight of from about 1,000 or less to about 5,000,000, preferably 1,000 to
30 1.5 million, and a molecular weight distribution of from about 1.5 to about 15.0, preferably less than 5 and most preferably less than 4.

In a preferred embodiment of the process of this invention the catalyst system is utilized in the liquid phase (slurry, solution, suspension or bulk phase or combination thereof), high pressure fluid phase or gas
35 phase polymerization of an olefin monomer. When utilized in a gas phase, slurry phase or suspension phase polymerization, the catalyst

systems will preferably be supported catalyst systems. See also, for example, U.S. Patent No. 5,057,475, WO 94/03506, which is incorporated herein by reference. Such catalyst systems can also be utilized in a gas phase process without a support as described in U. S. Patent 5,317,036.

5 Such catalyst systems can also include other well known additives such as, for example, scavengers. See, for example, U.S. Patent No. 5,153,157 and WO 94/07927 (April 14, 1994) which are incorporated herein by reference. These processes may be employed singularly or in series. The liquid phase process comprises the steps of contacting an ethylene and an
10 olefin monomer with the catalyst system in a suitable polymerization diluent and reacting the monomers in the presence of the catalyst system for a time and at a temperature sufficient to produce an ethylene- α -olefin copolymer of high molecular weight.

The monomers for such process comprise ethylene in combination
15 with an α -olefin having 3 to 20 carbon atoms, preferably 3 to 10 carbon atoms, most preferably 3 to 8 carbon atoms, for the production of an ethylene- α -olefin copolymer. It should be appreciated that the advantages as observed in an ethylene- α -olefin copolymer produced with a catalyst system of this invention would also be expected to be obtained
20 in a copolymer of different α -olefins wherein ethylene is not used as a monomer as viewed in comparison to a copolymer of the same or different α -olefins produced under similar polymerization conditions with a catalyst system which does not use a monocyclopentadienyl Group IV B metal compound as defined herein. Accordingly, although this
25 invention is described with reference to an ethylene- α -olefin copolymer and the advantages of the defined catalyst system for the production thereof, this invention is not to be understood to be limited to the production of an ethylene- α -olefin copolymer, but instead the catalyst system hereof is to be understood to be advantageous in the same respects
30 to the production of a copolymer composed of two or more C₃ or higher α -olefin monomers. Copolymers of higher α -olefin such as propylene, butene, styrene or higher α -olefins, cyclic olefins and diolefins can also be prepared. Conditions most preferred for the homo- or copolymerization of ethylene are those wherein ethylene is submitted to the reaction zone at
35 pressures of from about 0.019 psia to about 50,000 psia and the reaction temperature is maintained at from about -100°C to about 300°C. Where

the activator is an alumoxane, the aluminum to transition metal molar ratio is preferably from about 1:1 to 20,000 to 1. A more preferable range would be 1:1 to 2000:1. The reaction time is preferably from about 10 seconds to about 4 hours.

5 Without limiting in any way the scope of the invention, one means for carrying out the process of the present invention for production of a copolymer is as follows: in a stirred-tank reactor liquid α -olefin monomer is introduced, such as 1-butene. The catalyst system is introduced via
10 nozzles in either the vapor or liquid phase. Feed ethylene gas is introduced either into the vapor phase of the reactor, or sparged into the liquid phase as is well known in the art. The reactor contains a liquid phase composed substantially of liquid α -olefin comonomer, together with dissolved ethylene gas, and a vapor phase containing vapors of all monomers. The reactor temperature and pressure may be controlled via
15 reflux of vaporizing α -olefin monomer (autorefrigeration), as well as by cooling coils, jackets, etc. The polymerization rate is controlled by the concentration of catalyst. The ethylene content of the polymer product is determined by the ratio of ethylene to α -olefin comonomer in the reactor, which is controlled by manipulating the relative feed rates of these
20 components to the reactor.

Examples

In the examples which illustrate the practice of the invention the analytical techniques described below were employed for the analysis of
25 the resulting polyolefin products. Molecular weight determinations for polyolefin products were made by Gel Permeation Chromatography (GPC) according to the following technique. Molecular weights and molecular weight distributions were measured using a Waters 150-CV gel permeation chromatograph equipped with a differential refractive index
30 (DRI) detector. The system was used at 145°C with 1,2,4-trichlorobenzene as the mobile phase. Three Shodex (Showa Denko America, Inc.) mixed bed columns (AT-80 M/S) were used in series. This general technique is discussed in "Liquid Chromatography of Polymers and Related Materials III", J. Cazes editor, Marcel Dekker, 1981, p. 207, which is
35 incorporated herein by reference. No corrections for column spreading were employed; however, data on generally accepted standards, e.g.

National Bureau of Standards Polyethylene 1475 demonstrated that such corrections on M_w/M_n (= MWD) were within 0.1 units. M_w/M_n was calculated from elution times. The numerical analyses were performed using waters Expert Ease software package

- 5 The following examples are intended to illustrate specific embodiments of the invention and are not intended to limit the scope of the invention.

Experimental Section

- 10 All procedures were performed under an inert atmosphere of helium or nitrogen. Solvent choices were often optional, for example, in most cases, either pentane or 30-60 petroleum ether can be interchanged. The lithiated amides were prepared from the corresponding amines and either $n\text{-BuLi}$ or MeLi . Published methods for preparing LiHC_5Me_4 include C. M. Fendrick et al., *Organometallics* 1984, 3, 819 and F. H. Köhler and K. H. Doll, *Z. Naturforsch* 1982, 37b, 144. Other lithiated substituted cyclopentadienyl compounds are typically prepared from the corresponding cyclopentadienyl ligand and $n\text{-BuLi}$ or MeLi , or by reaction of MeLi with the proper fulvene. TiCl_4 was typically used in its etherated form. The etherate can be prepared by simply adding TiCl_4 to ether and filtering off the solid product which is then vacuum dried. TiCl_4 , amines, silanes, substituted and unsubstituted cyclopentadienyl compounds or precursors, and lithium reagents were purchased from Aldrich Chemical Company or Petrarch Systems. Activator components were purchased or prepared from known literature methods. The transition metal compounds $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{N-t-Bu})\text{TiCl}_2$ (Compound A) and $\text{Me}_2\text{Si}(\text{Me}_4\text{C}_5)(\text{N-c-C}_{12}\text{H}_{23})\text{TiCl}_2$ (Compound C), both of which are used as comparative examples, were prepared as described in US Patent number 5,264,405.

30

Example B - Compound B

- Part 1. $\text{C}_5\text{Me}_4\text{HLi}$ (10.0 g, 0.078 mol) was slowly added to a Me_2SiCl_2 (11.5 ml, 0.095 mol, in 225 ml of tetrahydrofuran (thf) solution). The solution was stirred for one hour to assure a complete reaction. The solvent was then removed in vacuo. Pentane was added to precipitate the LiCl . The mixture was filtered through Celite and the solvent was
- 35

removed from the filtrate in vacuo. $(C_5Me_4H)SiMe_2Cl$ (15.34 g, 0.071 mol) was recovered as a pale yellow liquid.

Part 2: $(C_5Me_4H)SiMe_2Cl$ (6.0 g, 0.028 mol) was diluted in ~ 150 ml thf. $LiHN-C_{10}H_{15}$ (lithiated 1-adamantylamine, 4.38 g, 0.028 mol) was added and the reaction mixture was allowed to stir for two hours. The solvent was removed via vacuum, and ~ 100 ml of ether was added. To this, 34 ml of MeLi (~ 1.4 M in ether, 0.048 mol) was added and the reaction mixture was stirred for three hours. The mixture was cooled to $-30^\circ C$ and $TiCl_4 \cdot 2Et_2O$ (7.74 g, 0.023 mol) was slowly added and the reaction mixture was allowed to stir overnight. The solvent was removed via vacuum and pentane was added. This mixture was filtered through Celite to remove the LiCl. The filtrate was reduced in volume and cooled to $-30^\circ C$ to induce precipitation of the product. The product was filtered off and washed with cold pentane yielding 1.7 g (3.8 mmol) of the yellow solid, $Me_2Si(Me_4C_5)(N-C_{10}H_{15})TiCl_2$.

Comparative Example D - Compound D

Part 1: C_5Me_4HLi (10.0 g, 0.078 mol) dissolved in ~ 150 ml thf was reacted with Ph_2SiCl_2 (19.75 g, 0.078 mol). The solution was stirred for three hours to assure a complete reaction. The solvent was then removed in vacuo. Petroleum ether was added to precipitate the LiCl. The mixture was filtered through Celite and the solvent was removed from the filtrate in vacuo. $(C_5Me_4H)SiPh_2Cl$ (22.0 g, 0.65 mol) was recovered as a pale yellow liquid.

Part 2: $LiHN-t-Bu$ (1.4 g, 0.0177 mol) was slowly added to $(C_5Me_4H)SiPh_2Cl$ (6.0 g, 0.0177 mol) in ~ 100 ml of thf. After stirring for two hours, the solvent was removed via vacuum and replaced with ~ 150 ml of ether. Assuming an 85% yield of $(C_5Me_4H)SiPh_2(HN-t-Bu)$ (0.015 mmol), 21 ml of 1.4 M MeLi (0.0294 mmol) was added and allowed to stir for three hours. The solution was then chilled to $-30^\circ C$ and 4.93 g of $TiCl_4 \cdot 2Et_2O$ (0.0146 mol) was added. The mixture was stirred overnight under ambient conditions.

Isolation of the product involved removing the solvent from the reaction mixture, adding pentane and filtering the mixture to remove the LiCl byproduct. The pentane filtrate was reduced in volume and the solution was chilled to $-30^\circ C$ to induce crystallization. The product was

filtered off, washed with cold pentane, and dried to give 1.8 g of the yellow solid, $\text{Ph}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{N}-t\text{-Bu})\text{TiCl}_2$ (3.7 mmol).

Example E - Compound E

5 Part 1: $(\text{C}_5\text{Me}_4\text{H})\text{SiPh}_2\text{Cl}$ was prepared as described in Example D, Part 1.

Part 2: $\text{LiHN}-\text{C}_{10}\text{H}_{15}$ (lithiated 1-adamantylamine, 2.78 g, 0.0177 mol) was slowly added to $(\text{C}_5\text{Me}_4\text{H})\text{SiPh}_2\text{Cl}$ (6.0 g, 0.0177 mol) in ~ 100 ml of thf. After stirring for two hours, the solvent was removed via
10 vacuum and replaced with ~ 150 ml of ether. Assuming an 85% yield of $(\text{C}_5\text{Me}_4\text{H})\text{SiPh}_2\text{Cl}(\text{HN}-\text{C}_{10}\text{H}_{15})$ (0.015 mmol), 21.4 ml of 1.4 M MeLi (0.030 mmol) was added and allowed to stir for three hours. The solution was then chilled to -30°C and 4.79 g of $\text{TiCl}_4 \cdot 2\text{Et}_2\text{O}$ (0.0142 mol) was added. The mixture was stirred overnight under ambient conditions.

15 Isolation of the product involved removing the solvent from the reaction mixture, adding pentane and filtering the mixture to remove the LiCl byproduct. The pentane filtrate was reduced in volume and the solution was chilled to -30°C to induce crystallization. The product was filtered off, washed with cold pentane and methylene chloride, and dried
20 to give 3.2 g of the mustard yellow solid, $\text{Ph}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{N}-\text{C}_{10}\text{H}_{15})\text{TiCl}_2$ (5.6 mmol).

Comparative Example F - Compound F

Part 1: $(\text{C}_5\text{Me}_4\text{H})\text{SiPh}_2\text{Cl}$ was prepared as described in
25 Example D, Part 1.

Part 2: $\text{LiHN}-c\text{-C}_{12}\text{H}_{23}$ (lithiated cyclododecylamine, 3.35 g, 0.0177 mol) was slowly added to $(\text{C}_5\text{Me}_4\text{H})\text{SiPh}_2\text{Cl}$ (6.0 g, 0.0177 mol) in ~ 150 ml of thf. After stirring for two hours, the solvent was removed via vacuum and replaced with ~ 150 ml of ether. Assuming an 85% yield
30 of $(\text{C}_5\text{Me}_4\text{H})\text{SiPh}_2\text{Cl}(\text{HN}-c\text{-C}_{12}\text{H}_{23})$ (0.015 mmol) 22 ml of 1.4 M MeLi (0.031 mmol) was added and allowed to stir for three hours. The solution was then chilled to -30°C and 4.97 g of $\text{TiCl}_4 \cdot 2\text{Et}_2\text{O}$ (0.0147 mol) was added. The mixture was stirred overnight under ambient conditions.

 Isolation of the product involved removing the solvent from the
35 reaction mixture, adding pentane and filtering the mixture to remove the LiCl byproduct. The pentane filtrate was reduced in volume and the

solution was chilled to -30°C to induce crystallization. The product was filtered off, washed with cold pentane, and dried to give 2.8 g of the yellow solid, $\text{Ph}_2\text{Si}(\text{C}_5\text{Me}_4)(\text{N-c-C}_{12}\text{H}_{23})\text{TiCl}_2$ (4.6 mmol).

5 Example G - Compound G

Part 1: $t\text{-BuC}_5\text{H}_4\text{Li}$ (10.0 g, 0.084 mol) was slowly added to a Me_2SiCl_2 (13.0 g, 0.101 mol, in 60 ml of tetrahydrofuran solution). The solution was stirred for 2 hours to assure a complete reaction. The solvent was then removed in vacuo. Pentane was added to precipitate the LiCl .
10 The mixture was filtered through Celite and the solvent was removed from the filtrate in vacuo. $(t\text{-BuC}_5\text{H}_4)\text{SiMe}_2\text{Cl}$ (15.9 g, 0.074 mol) was recovered as a pale yellow liquid.

Part 2: $(t\text{-BuC}_5\text{H}_4)\text{SiMe}_2\text{Cl}$ (6.0 g, 0.028 mol) was diluted in ~125 ml THF. $\text{LiHN-C}_{10}\text{H}_{15}$ (lithiated 1-adamantylamine, 4.72 g, 0.030 mol)
15 was added and the reaction mixture was allowed to stir for three hours. The solvent was removed via vacuum, and ~150 ml of ether was added. To this, 40.7 ml of MeLi (~1.4 M in ether, 0.057 mol) was added and the reaction mixture was stirred for 3 hours. The mixture was cooled to -30°C and $\text{TiCl}_4 \cdot 2\text{Et}_2\text{O}$ (9.26 g, 0.027 mol) was slowly added and the reaction
20 mixture was allowed to stir overnight. The solvent was removed via vacuum and pentane was added. This mixture was filtered through Celite to remove the LiCl . The filtrate was reduced in volume and cooled to -30°C to induce crystallization of the product. The product was filtered off and washed with cold pentane yielding 3.0 g (6.7 mmol) of the yellow
25 solid, $\text{Me}_2\text{Si}(t\text{-BuC}_5\text{H}_3)(\text{N-C}_{10}\text{H}_{15})\text{TiCl}_2$.

Example H - Compound H

$\text{Me}_2\text{Si}(t\text{-BuC}_5\text{H}_3)(\text{N-C}_{10}\text{H}_{15})\text{TiMe}_2$ was prepared by adding a stoichiometric amount of MeLi (~1.4 M in ether) to $\text{Me}_2\text{Si}(t\text{-BuC}_5\text{H}_3)(\text{N-C}_{10}\text{H}_{15})\text{TiCl}_2$ (1.0 g, 2.24 mmol, Compound G from Example G)
30 suspended in pentane. The solvent was removed via vacuum and pentane was added to precipitate the LiCl which was filtered off. The filtrate was reduced in volume and cooled to -30°C to precipitate the product. $\text{Me}_2\text{Si}(t\text{-BuC}_5\text{H}_3)(\text{N-C}_{10}\text{H}_{15})\text{TiMe}_2$ (0.36 g, 0.88 mmol) was
35 isolated.

Example I - Compound I

Me₂Si(Me₄C₅)(N-C₁₀H₁₅)TiMe₂ was prepared by adding a stoichiometric amount of MeLi (~1.4M in ether) to Me₂Si(Me₄C₅)(N-C₁₀H₁₅)TiCl₂ (1.0 g, 2.24 mmol, Compound B from Example B) suspended in ether. The solvent was removed via vacuum and pentane was added to precipitate the LiCl which was filtered off. The filtrate was reduced in volume and cooled to -30°C to precipitate the product. Me₂Si(Me₄C₅)(N-C₁₀H₁₅)TiMe₂ (0.33 g, 0.81 mmol) was isolated.

Polymerization Examples 2, 4 and 6; Comparative Examples 1, 3, 5 and 7

The polymerization reactions were performed in a stirred 1 L steel autoclave reaction vessel which was equipped to perform continuous Ziegler Natta polymerization reactions at pressures up to 2500 bar and temperatures up to 300°C. The reaction system was supplied with a thermocouple and pressure transducer to measure temperature and pressure continuously, and with means to supply continuously purified compressed ethylene and 1-butene, 1-hexene, propylene or any other desired unsaturated comonomer. Equipment for continuously introducing a measured flow of catalyst solution, and equipment for rapidly venting and quenching the reaction, and of collecting the polymer product were also a part of the reaction system. Without the addition of a solvent, the polymerization was performed with a 1.6 molar ratio of 1-butene to ethylene pressurized at 1300 bar. No hydrogen was used. The catalyst solution was prepared by mixing a specified amount of solid transition metal component with a methylalumoxane solution further diluted in toluene under an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate which resulted in the desired reactor temperature of 180°C. The reactor contents were stirred at 1,000 rpm and the reactor mass flow rate used was 40 kg/hr. Exact run conditions including catalysts preparation [transition metal component (TMC) (g), weight percent methylalumoxane (MAO) and volume used (L), total catalyst solution volume prepared (L), and concentration (g TMC/L) and (g MAO/L)], catalyst feed rate (L/hr), polymer production rate (kg polymer/hr), molar Al/M ratio, TMC productivity (kg polymer/g TMC), TMC productivity (kg polymer/mol

TMC), catalyst productivity (kg polymer/g catalyst) and polymer characteristics including weight average MW (daltons), molecular weight distribution (M_w/M_n =MWD), melt index (g/10 minutes at 190°C), weight percent comonomer (determined by ¹H NMR), and "catalyst reactivity ratios" (r₁) are collected in Table 1. "Catalyst reactivity ratios" were calculated as (1-butene/ethylene molar ratio in reactor-feed) x (ethylene/1-butene molar ratio in the polymer). An example of how to use the information contained in Table 1 follows using Example 1.

Using the reactor design as described above, and using a molar ratio of 1-butene to ethylene of 1.6 without the addition of a solvent, the temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 180°C. The catalyst solution was prepared by mixing 0.878 g of solid compound A with 0.75 L of a 30 weight percent methylalumoxane solution with added toluene to give a total volume of 10L. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate of 0.84 L/hr which resulted in a temperature of 180°C in the reactor. During this run, ethylene and 1-butene were pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1,000 rpm, and the mass flow rate through the reactor was 40 kg/hr. The yield of polymer product was 4.3 kg/hr of an ethylene-1-butene copolymer which had a weight average molecular weight of 61,000 daltons, a molecular weight distribution of 3.346, and a comonomer incorporation of 32.4 weight percent butene measured by H NMR. The polymer melt index measured at 190°C was 6.6 g/10 minutes. The catalyst reactivity ratio of ethylene to butene was calculated to be 6.7. Productivities were calculated at 59 kg polymer/g A, 21,600 kg polymer/mol A, and 0.26 kg polymer/g catalyst.

30 EXAMPLE G - Ionic Invention Catalyst and Polymerization of Cyclic Olefin Copolymer

Me₂Si(t-BuCp)(N-C₁₀H₁₅)TiMe₂ (40.0 mg) (compound G) was weighed out under inert atmosphere and N,N-Dimethylanilinium tetrakis-perfluorophenyl boron, [(DMAH)] [B(pfp)₄], activator was added to give a slight molar excess of the transition metal complex. Dry toluene (2 mL) was added by pipette and the mixture allowed to stand with

occasional stirring until activation was complete (10 to 20 min.). The resulting mixture was septa sealed and ready for transfer to the reactor via cannula.

Dry toluene (0.8 liter) was transferred to a clean, dry and N₂ purged 2 liter autoclave reactor using air sensitive technique. The solvent was stirred under a continued slow N₂ purge while the reactor was equilibrated at 60°C. Triisobutylaluminum (TIBA) was added as a scavenger by diluting 0.5 mL of a 1 M solution in toluene with additional toluene (10 to 20 mL) and transferring to the reactor via cannula through the purge port using standard air sensitive technique. Norbornene (53 g) was added to the reactor as a concentrated solution in toluene (86 wt.%) via cannula through the purge port using standard air sensitive technique. The N₂ purge was shut off simultaneously as the reactor was sealed. Ethylene gas (1 bar) was added to the reactor until the solution was saturated. (Molar feed ratio Norbornene:Ethylene = 3.9 : 1.) The ethylene regulator and flow controller were set to maintain the 15 psig ethylene pressure with a replenishing flow. The reactor was then quickly vented and 18.0 g of the pre-activated catalyst was added to the reactor via cannula through the purge port. The port was then sealed and the ethylene pressure quickly returned to 15 psig by opening the flow controller. The mixture was stirred at 60°C for 20 minutes.

The reaction was quenched by rapid venting of the reactor and its contents poured into one liter of rapidly stirring acetone. The resulting white solid polymer was washed, separated by filtration, and dried in a vacuum oven overnight (60°C, -30 in. Hg). Copolymer (24.2 g) was obtained that had a glass transition temperature of 85°C, $M_w = 1,380,000$, $MWD = 1.42$.


TABLE 1

No	TMC	TMC (g)	MAO (Wt.%)	MAO (L)	Total Vol (L)	TMC (g/L)	MAO (g/L)	Feed Rate (L/hr)	Production Rate (kg/hr)	Al/M (molar)	TMC Prod (kg/g)	TMC Prod (kg/mol)	Catalyst Prod (kg/g)	MW D	MI	WL% C ₄	n	
C1	A	0.878	30	0.75	10	0.0878	19.6	0.84	4.3	1416	59	21,601	0.28	81,000	3,346	6.6	32.4	6.7
2	B	0.785	30	0.60	8	0.0858	19.6	0.48	3.4	1575	76	33,998	0.37	88,700	3,168	2.2	34.2	6.2
C3	C	1.532	30	1.00	20	0.0768	13.1	1.61	5.4	1405	43	20,757	0.25	76,800	2,858	6.0	40.0	4.8
4	C	0.513	30	0.33	10	0.0513	8.6	1.59	4.1	1385	50	23,758	0.29	81,800	2,987	4.7	41.1	4.6
C5	D	1.080	30	0.70	11	0.0982	16.6	1.42	4.1	1437	29	14,307	0.17	59,100	3,617	7.2	38.6	5.1
6	E	1.801	30	1.00	18	0.1001	14.5	1.15	5.0	1428	43	24,792	0.30	68,500	3,280	8.1	36.0	5.7
C7	F	1.547	30	0.80	10	0.1547	20.9	1.72	4.4	1402	16	9,880	0.12	72,800	2,925	8.3	42.4	4.3

CLAIMS:


1. A compound of the formula:

Formula I



or

Formula II



wherein:

M is Zr, Hf or Ti;

$(C_5H_{4-x}R_x)$ is a cyclopentadienyl ring which is substituted with from zero to four substituent groups R, "x" is 0, 1, 2, 3, or 4 denoting the degree of substitution, and each substituent group R is, independently, a radical selected from C_1 - C_{20} hydrocarbyl radicals; substituted C_1 - C_{20} hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical, or an aryloxy radical; C_1 - C_{20} hydrocarbyl-substituted metalloid radicals wherein the metalloid is selected from Group IV A of the Periodic Table of Elements; halogen radicals; amido radicals; phosphido radicals; alkoxy radicals; aryloxy radicals; alkylborido radicals; or $(C_5H_{4-x}R_x)$ is a cyclopentadienyl ring in which at least two adjacent R-groups are joined together and along with the carbon atoms to which they are attached form a C_4 - C_{20} ring system;

R' is a radical selected from C_4 - C_{30} alicyclic hydrocarbyl radicals wherein one or more hydrogen atoms may be replaced by radicals selected from halogen, amido, phosphido, alkoxy, aryloxy or any other radical

containing a Lewis acidic or basic functionality, with the proviso that R' is covalently bonded to the nitrogen atom through a tertiary carbon atom;

each Q is be independently selected from univalent anionic ligands, or both Q together may be an alkylidene or a cyclometallated hydrocarbyl or any other divalent anionic chelating ligand with the proviso that where any Q is a hydrocarbyl such Q is not a substituted or unsubstituted cyclopentadienyl radical;

T is a covalent bridging group containing a Group IV A or V A element;


L is a neutral Lewis base which is optionally covalently bonded to one or both Q;

"w" is a number from 0 to 3; and

M' has the same meaning as M, and Q' has the same meaning as Q.

2. A compound of the formula:

Formula III



wherein:

M represents Ti, Hf or Zr;

(C₅H_{4-x}R_x) is a cyclopentadienyl ring which is substituted with from zero to four substituent groups R, "x" is 0, 1, 2, 3, or 4 denoting the degree of substitution, and each substituent group R is, independently, a radical selected C₁-C₂₀ hydrocarbyl radicals; substituted C₁-C₂₀ hydrocarbyl radicals wherein one or more hydrogen atoms is replaced by a halogen radical, an amido radical, a phosphido radical, an alkoxy radical, and an aryloxy radical, C₁-C₂₀ hydrocarbyl-substituted metalloid radicals wherein the metalloid is selected from Group IV A of the Periodic Table of Elements; halogen radicals; amido radicals; phosphido radicals; alkoxy radicals; aryloxy radicals; and alkylborido radicals; or (C₅H_{4-x}R_x) is a cyclopentadienyl ring in which at least two adjacent R-groups are joined together and along with the carbon atoms to which they are attached, form a C₄-C₂₀ ring system;

each of R^1 and R^2 are independently selected from C_1 - C_{20} hydrocarbyl radicals;

each Q is independently selected from halide, hydride, substituted or unsubstituted C_1 - C_{20} hydrocarbyl radicals, alkoxide, aryloxy, amide and phosphid radicals with the proviso that Q is not a substituted or unsubstituted cyclopentadienyl radical;

R' is selected from C_4 - C_{30} alicyclic hydrocarbyl radicals with the proviso that R' is covalently bonded to the nitrogen atom through a tertiary carbon atom;

T is Si or Ge;


L is a neutral Lewis base which is optionally covalently bonded to one or both Q; and

w is a number from 0 to 3.

3. The compound of Claim 2 wherein M is Ti.

4. A compound of the formula:

Formula IV



wherein: M is Zr, Hf, or Ti;

T is selected from Si or Ge;

each of R^1 and R^2 are independently selected from C_1 - C_{20} hydrocarbyl radicals;

each R^3 is independently selected from hydrogen; C_1 - C_{20} alkyl; C_3 - C_{20} cycloalkyl; C_6 - C_{22} aryl; halogen; amido; phosphido; alkoxy; borido; and the like radicals; or combinations thereof;

u is an integer of from 0 to 6;

each R^4 is independently selected from hydrogen; halogen, C_1 - C_{10} alkyl; C_3 - C_{10} cycloalkyl; C_6 - C_{22} aryl; amido; alkoxy; aryloxy or combinations thereof and the like radicals, or two R groups along with the carbon atom or atoms to which they are attached, form a saturated or partially saturated alicyclic group or form an aryl group;

each Q is independently selected from halide, hydride, substituted or unsubstituted C_1 - C_{20} hydrocarbyl radicals; alkoxide; amide; and phosphide radicals, with the proviso that Q is not a substituted or unsubstituted cyclopentadienyl radical;


L is a neutral Lewis base which is optionally covalently bonded to one or both Q ;

w is a number from 0 to 3; and

x is an integer of from 0 to 4.

5. A compound of the formula:

Formula V



wherein: M is Zr, Hf or Ti;

T is selected from radicals of the formula $(CR_5R_6)_y$ wherein R^5 and R^6 are independently selected from hydrogen and C1-C20 hydrocarbyl radicals; and wherein y is 1, 2 or 3;

each R^3 is independently selected from hydrogen; C₁-C₂₀ alkyl; C₃-C₂₀ cycloalkyl; C₆-C₂₂ aryl; halogen; amido; phosphido; alkoxy; borido; or combinations thereof;

each Q is independently selected from hydrogen; halogen; C₁-C₂₀ alkyl; C₆-C₂₂ aryl; C₃-C₂₀ cycloalkyl; alkoxy; aryloxy; amido; and phosphido radicals; or combinations thereof

each R^4 is independently selected from hydrogen; halogen; C₁-C₁₀ alkyl; C₃-C₁₀ cycloalkyl; C₆-C₂₂ aryl; amido; alkoxy; and combinations thereof; or two R groups along with the carbon atom or atoms to which they are attached, form a saturated or partially saturated alicyclic group or form an aryl group;

L is a neutral Lewis base which is optionally covalently bonded to one or both Q;

u is an integer of from 0 to 6;

w is an integer from 0 to 3; and

x is an integer of from 0 to 4.

6. A catalyst system comprising a compound of Claim 1 and an activator.
7. A catalyst system comprising a compound of Claim 2 and an activator.
8. A catalyst system comprising the compound of Claim 4 and an activator.
9. A catalyst system comprising a compound of Claim 5 and an activator.
10. The catalyst system of Claim 6 wherein the activator is an activator comprising a cation and a non-coordinating compatible anion and Q is selected from hydride and substituted and unsubstituted C₁-C₂₀ hydrocarbyl radicals.
11. The catalyst system of Claim 6 wherein the activator is an alumoxane.
12. The catalyst system of Claim 7 wherein the activator is an activator comprising a cation and a non-coordinating compatible anion and Q is

selected from hydride and substituted and unsubstituted C₁-C₂₀ hydrocarbyl radicals.

13. The catalyst system of Claim 7 wherein the activator is an alumoxane.

14. The catalyst system of Claim 8 wherein the activator is an activator comprising a cation and a non-coordinating compatible anion and Q is selected from hydride and substituted and unsubstituted C₁-C₂₀ hydrocarbyl radicals.

15. The catalyst system of Claim 8 wherein the activator is an alumoxane.

16. The catalyst system of Claim 9 wherein the activator is an activator comprising a cation and a non-coordinating compatible anion and Q is selected from hydride and substituted and unsubstituted C₁-C₂₀ hydrocarbyl radicals.

17. The catalyst system of Claim 9 wherein the activator is an alumoxane.

18. An ionic catalyst system comprising a cation derived from a compound of Claim 1 and a bulky, compatible, non-coordinating anion.

19. An ionic catalyst system comprising a cation derived from a compound of Claim 2 and a bulky, compatible, non-coordinating anion.

20. An ionic catalyst system comprising a cation derived from a compound of Claim 4 and a bulky, compatible, non-coordinating anion.

21. An ionic catalyst system comprising a cation derived from a compound of Claim 5 and a bulky, compatible, non-coordinating anion.

22. A method for producing an ethylene- α -olefin copolymer of greater than 20 wt. % α -olefin content, comprising the steps of:

(a) supplying ethylene and a liquid α -olefin to a reaction zone at a molar ratio of α -olefin to ethylene of less than 2:1 in an amount sufficient to maintain a pressure within the reaction zone of from about 0.019 to about 50,000 psia; and

(b) introducing into contact with the ethylene and α -olefin in the reaction zone a catalyst system of Claim 6.

23. A method for producing an ethylene- α -olefin copolymer of greater than 20 wt.% α -olefin content, comprising the steps of:

(a) supplying ethylene and an α -olefin to a reaction zone at a molar ratio of α -olefin to ethylene of less than 2:1 in an amount sufficient to maintain a pressure within the reaction zone of from about 0.019 to about 50,000 psia; and

(b) introducing into contact with the ethylene and α -olefin in the reaction zone a catalyst system of Claim 10;

said catalyst system being introduced in an amount sufficient to maintain a temperature within the reaction zone of from about -100 to about 300°C.

24. The method of Claim 18 wherein the activator is a non-coordinating compatible anion and Q is selected from hydride and substituted and unsubstituted C_1 - C_{20} hydrocarbyl radicals.

25. The method of Claim 18 wherein the activator is an alumoxane.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 95/07715

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08F10/00 C08F4/64 C07F17/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F C07F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO,A,94 07928 (THE DOW CHEMICAL COMPANY) 14 April 1994 see claim 1 -----	1-25

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another claim or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

4 September 1995

Date of mailing of the international search report

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Serravalle, M

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int'l. Application No

PCT/US 95/07715

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9407928	14-04-94	CA-A- 2146012	14-04-94
		EP-A- 0662979	19-07-95
		FJ-A- 951548	29-05-95
		NO-A- 951267	31-05-95
<hr/>			